



Quality differences in commercial charcoal

Dr. Carolin Fischer

NETZSCH-Gerätebau GmbH

Introduction

Summertime is barbecue time. But have you ever wondered which charcoal is best to use? The quality of charcoal can be characterized by the amount containing organic compounds, the ash content and energy released during combustion. These are all properties which can be determined using the simultaneous thermal analyzer NETZSCH STA. With the help of a TGA-DSC measurement, it is easy to check whether the price difference between products is justified by the quality.

For a comparison, three different kinds of commercial charcoal were selected: beech wood charcoal, brandname charcoal and a cheap charcoal from a discount shop.

Results and Discussion

The TGA-DSC measurements were performed with simultaneous thermal analyzer, STA, equipped with a TGA-DSC sample carrier type S. The different charcoal samples were heated as bulk samples to 550°C in an inert atmosphere and from 550°C to 950°C in an oxidizing atmosphere. For detailed measurement conditions, see table 1.

The results for the beech wood charcoal sample are plotted in figure 1. The three mass-loss steps were accompanied by energetic effects. The first mass-loss step, at 81°C, was probably caused by




Fig. 1: Temperature-dependent mass change (TGA, green), heat flow curve (DSC, blue) and rate of mass change (DTG, black) of beech wood charcoal

the release of water, whereas the second mass loss, at 411°C, is an indication of the pyrolysis of residual organic compounds. These events caused two endothermic effects at peak temperatures of 67°C and 394°C and enthalpies of 30 J/g and 5 J/g. The combustion of the remaining carbon under a synthetic air atmosphere resulted in a mass loss of 92% and an exothermic effect with an enthalpy of -23,315 J/g. This is not the complete combustion enthalpy, as an STA is an open system which emits part of the

generated energy with the purge gases and the released gases. This value can only be used for relative comparison. The residual mass related to the ash content amounted to 3%.

Figure 2 depicts the comparison of the TGA results for the different charcoal samples. The given temperature program led to two mass-loss steps for each sample under an inert atmosphere. In terms of water content, the brand-name charcoal showed the highest value, followed by the discounter charcoal and the beech wood charcoal.

Tab. 1 Measurement parameters

Parameter	Beech wood charcoal	Brand-name charcoal	Discounter charcoal	Beech wood
Temperature programm	RT to 550 °C, nitrogen 550 °C to 950 °C, oxidizing atmosphere			
Heating rate	20 K/min			
Gas flow	70 ml/min			
Crucible	Platinum with pierced lid			
Sample carrier	TG-DSC, type S			
Sample mass	9,49 mg	10,03 mg	9,94 mg	7,83 mg

The differing water content is most probably due to different storage conditions, but may also be caused by differences in the surfaces' properties which allow for the absorption of water.

In contrast, the proportion of organic compounds yields information about the level of completion of the production process for the charcoal and briquettes: The lower the organic content, the better the pyrolysis of the initial wood to charcoal during the production process, yielding a higher quality charcoal. Comparing the three samples, again the beech wood charcoal exhibited the lowest value, followed by the brand-name charcoal and the discounter charcoal. This process was not yet finished at 550°C for the discounter charcoal, meaning that the sample still contains organic compounds at this temperature.

After switching to an oxidizing atmosphere, the residual carbon was burnt with oxygen and released carbon dioxide and carbon monoxide. Also here, differences between the three samples were observed. A carbon content of over 90% was determined for the beech wood charcoal, whereas both the brand-name charcoal and the discounter charcoal showed values of around 75% carbon. A high carbon content indicates high purity of the charcoal.

Consequently, the three samples also differ in terms of their residual mass, which characterizes the ash content of the charcoal. Surprisingly, the brand-name charcoal yielded more than 10% ash, whereas the other two showed values between 3% and 5%. The ash content can also be seen as a criterion of quality. The lower the ash content, the less the initial proportion of unreactive side products like fillers or minerals.

The comparison of the DSC signals, depicted in figure 3, showed that the beech wood charcoal released the most heat during the oxidative combustion. As the samples were measured in an open, non-adiabatic system, these values cannot be regarded as the heat of combustion.

The measured enthalpy is significantly lower than the heat of combustion, as hot reaction gases leave the sample and take the released heat with them. However, the released heat can be used as a good relative comparison of the three samples.




Fig. 2: Temperature-dependent mass changes (TGA) and gas atmosphere of the brand-name charcoal briquettes, beech wood charcoal and discounter charcoal




Fig. 3: Temperature-dependent heat flow curves (DSC) and gas atmosphere of the brand-name charcoal, beech wood charcoal and discounter charcoal




Fig. 4: Temperature-dependent mass change (TGA), heat-flow curve (DSC) and gas atmosphere of beech wood (black) and beech wood charcoal (green)

A further measurement was carried out on a beech wood sample; see figure 4. As expected, the amount of water and the organic content were much higher. The first mass-loss step, which refers to water, resulted in 5.13%. The increase in temperature led to a two-stage decomposition of the organic content amounting to 68.35% in total. The comparison to the beech wood charcoal showed that the charcoal production process pyrolyzing the wood was nearly complete. The organic content was decreased from around 68% to less than 3%. The lower carbon content of the wood is also reflected in the exothermic enthalpy detected during the oxidative combustion.

Summary

Quality characteristics of charcoals such as moisture, ash content and released heat can be detected with the help of the simultaneous thermal analyzer, STA, by NETZSCH Analyzing & Testing. It was possible to demonstrate the high quality of the beech wood charcoal with regard to these properties, whereas the brand-name charcoal did not show significantly better values than a discounter charcoal sample in this particular case. Additionally, the TGA-DSC method is suited to control completion of the charcoal production process concerning the pyrolysis of organic materials.

Enjoy your barbecue!